



Element Materials Technology P 714 892 1961
 15062 Bolsa Chica F 714 892 8159
 Huntington Beach, CA T 888 786 7555
 92649-1023 USA info.hb@element.com
 element.com

Contact: Viola Villa
 C.R. Laurence Co., Inc.
 2200 E. 55th St.
 LOS ANGELES, CA 90058

*****PARTIAL TEST CERTIFICATE — EAR-CONTROLLED DATA — 9/26/2017*****

Date: 9/26/2017
 Purchase Order Number: 1188401
 Work Order Number: CRL001-03-22-05635-1

Sample ID:	A1
P/N:	CRL Security Screen
Job#:	PTC629158
Description:	12" X 12" Black Powder Coated Stainless Steel Mesh
Specification:	AS2331.3.1 / ASTM-B117

SALT SPRAY

Customer Requirement:	For Information only
Test Method:	ASTM B117-16
Quantity Tested:	1
Total Hours:	1000
Angle:	15° - 30° from vertical

Salt spray was performed in a salt spray chamber using a 5% +/- 1% salt solution at 95° +/- 3° Fahrenheit, in accordance with ASTM B117-16. The results are as follows:

Samples showed no visual evidence of corrosion at the end of 1000 hours of exposure to salt spray corrosion testing.

SALT SPRAY

Customer Requirement:	For Information only
Test Method:	ASTM B117-16
Quantity Tested:	1
Total Hours:	2500
Angle:	15° - 30° from vertical

Salt spray was performed in a salt spray chamber using a 5% +/- 1% salt solution at 95° +/- 3° Fahrenheit, in accordance with ASTM B117-16. The results are as follows:

Samples showed no visual evidence of corrosion at the end of 2500 hours of exposure to salt spray corrosion testing.

SALT SPRAY

Customer Requirement:	For Information only
Test Method:	ASTM B117-16
Quantity Tested:	1
Total Hours:	5000
Angle:	15° - 30° from vertical

Salt spray was performed in a salt spray chamber using a 5% +/- 1% salt solution at 95° +/- 3° Fahrenheit, in accordance with ASTM B117-16. The results are as follows:

Samples showed no visual evidence of corrosion at the end of 5000 hours of exposure to salt spray corrosion testing.

FOR INFORMATION ONLY

This document contains technical data whose export and re-export/ retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval may be required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

Respectfully Submitted

Grace G. Humphreys
 Grace G. Humphreys
 Quality Administrator

15062 Bolsa Chica, Huntington Beach, CA 92649
 (714) 892-1961 ph • (714) 892-8159 fax • www.element.com

The information contained in this certification represents only the material submitted and is certified only for the quantities tested. Reproduction except in full is reserved pending written approval. The recording of false, fictitious, or fraudulent statements or entries on the certificate may be punishable as a felony under federal law. All testing was performed in a mercury free environment. **All testing performed in accordance with the latest edition of the applicable ASTM, or other Federal Test Method in effect at the time of test.**



Element Materials Technology
 15062 Bolsa Chica
 Huntington Beach, CA
 92649-1023 USA

P 714 892 1961
 F 714 892 8159
 T 888 786 7555
 info.hb@element.com
 element.com

Contact: Viola Villa
 C.R. Laurence Co., Inc.
 2200 E. 55th St.
 LOS ANGELES, CA 90058

TEST CERTIFICATE — EAR-CONTROLLED DATA

Date: 4/4/2018
 Purchase Order Number: 1188401
 Work Order Number: CRL001-03-22-05635-1

Sample ID:	A1
P/N:	CRL Security Screen
Job#:	PTC629158
Description:	12" X 12" Black Powder Coated Stainless Steel Mesh
Specification:	FOR INFORMATION ONLY, REF: AS2331.3.1 / ASTM-B117

SALT SPRAY

Requirement:	For Information Only
Test Method:	ASTM B117-16
Quantity Tested:	1
Total Hours:	10000
Angle:	15° - 30° from vertical

Salt spray was performed in a salt spray chamber using a 5% +/- 1% salt solution at 95° +/- 3°F, in accordance with ASTM B117-16. The results are as follows:

Sample showed no visual evidence of corrosion at the end of 10000 hours of exposure to salt spray corrosion testing.

FOR INFORMATION ONLY

This document contains technical data whose export and re-export/ retransfer is subject to control by the U.S. Department of Commerce under the Export Administration Act and the Export Administration Regulations. The Department of Commerce's prior written approval may be required for the export or re-export/retransfer of such technical data to any foreign person, foreign entity or foreign organization whether in the United States or abroad.

Respectfully Submitted

Grace G. Humphreys
 Grace G. Humphreys
 Quality Administrator

15062 Bolsa Chica, Huntington Beach, CA 92649
 (714) 892-1961 ph • (714) 892-8159 fax • www.element.com

Denotes non-conforming results. *Denotes change made from original test certificate.

The information contained in this certification represents only the material submitted and is certified only for the quantities tested. Reproduction except in full is reserved pending written approval. The recording of false, fictitious, or fraudulent statements or entries on the certificate may be punishable as a felony under federal law. All testing was performed in a mercury free environment. **All testing performed in accordance with the latest edition of the applicable ASTM, or other Federal Test Method in effect at the time of test.**